



# Cerafiber<sup>®</sup>, Cerachem<sup>®</sup> Bulks

## Product Data Sheet

### Product Description

Cerafiber Bulk is produced from a high purity blend of alumina and silica and is rated to 1260°C (2300°F).

Cerachem Bulk is produced from a blend of alumina, silica and zirconia and designed to resist excessive shrinkage at elevated temperatures and are rated to 1430°C (2600°F).

Our wide range of bulk and chopped fibres is resistant to most types of chemical attack. They are lightweight, strong and feature a low heat storage capacity for effective energy savings and excellent thermal shock resistance for use in difficult environments.

### Features

- Excellent resistance to thermal shock
- Fibres are opaque to infrared and so maintain their low thermal conductivity to high temperatures
- Fibres absorb very little energy on heating
- Fibres are high purity and highly corrosion resistant
- Fibres are highly resilient

### Applications

- Expansion joints
- Low mass kiln cars
- Tube seal fabrication
- Thermal and acoustical insulation
- Filtration media
- Reinforcement and filler for plastics, resins and paints
- Fillers for mastics, cements
- Raw materials for vacuum formed boards and shapes, felts and papers

# Cerafiber<sup>®</sup>, Cerachem<sup>®</sup> Bulks

## Product Data Sheet



	Cerafiber Bulk	Cerachem Bulk
Colour	White	White
Classification Temperature, °C (°F), EN1094-1 (2008)	1260 (2300)	1430 (2600)
Continuous Use Temperature, °C (°F)	1180 (2150)	1350 (2460)
Melting Temperature, °C (°F)	1760 (3200)	1760 (3200)
Specific Heat, kJ/kg•°C @ 980°C (BTU/lb•°F @ 1800°F)	1.13 (0.27)	1.13 (0.27)
Specific gravity, g/cm <sup>3</sup>	2.5	2.75
Average Fibre Diameter, µm	2.2 - 2.8	2.5 - 3.2
Fibre Index, %	48 - 58	48 - 58
<b>Chemical Analysis, %</b>		
Alumina, Al <sub>2</sub> O <sub>3</sub>	42 - 48	33 - 37
Silica, SiO <sub>2</sub>	52 - 58	48 - 52
Zirconium oxide, Zr <sub>2</sub> O <sub>3</sub>	-	13 - 17
Other	trace	trace

### Product Availability

Cerafiber and Cerachem Bulk Fibres are manufactured globally, but fibre grades and packaging vary by region. Please reference the table below and contact your regional Morgan Advanced Materials - Thermal Ceramics representative to provide specific packaging available for your local business needs.

Europe		Americas		Asia
Lubricated and Unlubricated bulk available in bales or bags		Lubricated (Grade 111) or Unlubricated (Grade 112) bulk available in bags		Lubricated or Unlubricated bulk available in bags
Grade	Description	Grade	Description	
G25	Chopped to medium length	HM-50	Hammer milled to long length	
G6	Chopped to short length	HM-25	Hammer milled to medium length	
		HM-12	Hammer milled to short length	

The product(s) represented are intended for industrial refractory applications. The values and application information in this datasheet are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product, and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials.