

# Cerafelt®

## Product Data Sheet



### Product Description

Cerafelt is an insulating refractory felt, manufactured with our Cerachem® fibres by hotpressing. Cerafelt is bonded with an organic binder which begins to burn out at 180°C (356°F).

This special binder makes Cerafelt particularly suitable for die-cutting operations. Semi rigid, it is neither brittle nor dusty. Cerafelt optimizes the manufacture of complex, die-cut shapes to close tolerances.

With a choice from eight densities and seven thicknesses, Cerafelt offers a grade to suit most requirements.

### Features

- Wide range of densities: eight grades from 48 up to 384 kg/m<sup>3</sup> (3 up to 24 pcf)
- High temperature resistance
- Very low thermal conductivity
- Particularly suited to cutting operations; with saw, water jet or by stamping
- Flexible or semi-rigid, depending on density selected
- Chemically stable
- High sound absorption properties
- Precise thicknesses
- Resistant to thermal shock
- Low heat storage

### Applications

- High temperature gaskets
- Expansion joints for furnace, kiln and boiler linings
- Die cut shapes for domestic appliances
- Thermal barrier media
- Insulating thermal break

Properties		Cerafelt
Region of Manufacture		EMEA
Color		Yellow
Classification Temperature, °C (°F), EN 1094-1 (2008)		1320 (2400)
Density, kg/m <sup>3</sup> , EN 1094-1 (2008)		
	Dry, as supplied	48, 64, 96, 128, 160, 192, 288, 384
Loss of Ignition, %		4-12
Permanent Linear Shrinkage, %, after 24 hours, ENV 1094-1		
	1260°C (2300°F)	2.5
	1320°C (2400°F)	3
Chemical Analysis, %		
	Alumina, Al <sub>2</sub> O <sub>3</sub>	35.1
	Silica, SiO <sub>2</sub>	49.7
	Zirconium oxide, ZrO <sub>2</sub>	14.7
	Others	0.35

Thermal Conductivity, W/m·K (BTU·in/hr·ft <sup>2</sup> ·°F), ASTM C201								
Density, kg/m <sup>3</sup>	48	64	96	128	160	192	288	384
300°C	0.11	0.10	0.08	0.08	0.07	0.07	0.07	0.06
500°C	0.20	0.17	0.14	0.12	0.11	0.11	0.10	0.10
700°C	0.33	0.27	0.21	0.18	0.16	0.15	0.13	0.13
900°C	0.51	0.41	0.31	0.25	0.22	0.20	0.17	0.15
1000°C	0.75	0.59	0.42	0.34	0.29	0.25	0.21	0.18

### Standard Dimensions and Availability

This Cerafelt Product is manufactured in EMEA.

Please check with your local Morgan Advanced Materials -Thermal Ceramics representative for your local business needs.

Thickness, mm (in)	Density, kg/m <sup>3</sup>							
	48	64	96	128	160	192	288	384
3 (0.12)				X	X	X	X	X
6 (0.24)		X	X	X	X	X	X	X
10 (0.4)		X	X	X	X	X	X	X
13 (0.52)	X	X	X	X	X	X	X	
19 (0.76)	X	X	X	X	X	X		
25 (1)	X	X	X	X	X	X		
38 (1.52)			X					

Whilst the values and application information in this datasheet are typical, they are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials - Thermal Ceramics.