

Product Description

Kaowool Pumpables are water-based, pliable, putty like materials composed of high temperature ceramic fibers, organic polymers, inorganic binders, and other proprietary ingredients. They are supplied premixed and ready to install from straight-sided 5 gallon pails using the HS-100 Extrusion or similar pump. Kaowool Pumpables can be used in hot or cold repairs of any deteriorated back-up insulation in ovens, furnaces, boilers, and process equipment, and as a hot-face repair of any cracks or gaps in existing refractory due to shrinkage. Kaowool Pumpables when dried form a hard rigid mass that provides good insulating properties, good strength and vibration resistance.

Kaowool Pumpable - Standard grade pumpable for applications up to 2000°F (1093°C)

Kaowool Pumpable XTP – A more fluid grade of pumpable for applications up to 2000°F (1093°C)

Kaowool Pumpable HT – High temperature grade for applications up to 2500°F (1371°C)

Kaowool Pumpable HS – An exceptionally strong and abrasion resistant refractory insulation for applications up to 2800°F (1538°C)

Features

- Hot spot repair
- One-component pumpable
- Ready to use
- Good damming ability
- Highly insulating
- Four unique grades available
- Freeze/Thaw stable (except Kaowool Pumpable XTP)

Applications

- Hot or cold repair to refractory backup insulation
- Hot or cold repair of boiler insulation, sidewalls, and penthouses
- Brick kiln crown and walls
- Coke oven jambs and seals

Installation Information

Kaowool Pumpables are installed under pressure using pumping equipment such as the HS-100 Extrusion Pump. A back-pressure gauge is recommended when pumping Kaowool Pumpables to repair a backup lining. This will protect against damage to the hot face lining. The HS-100 Extrusion Pump is available for purchase and can also be rented on a weekly basis.

Handling

Pails should be kept sealed to avoid hardening. Kaowool Pumpable XTP will be damaged if allowed to freeze. Normal shelf life is minimum six to twelve months depending on grade in unopened containers that have been properly stored.

Product Name	Kaowool Pumpable	Kaowool Pumpable XTP	Kaowool Pumpable HT	Kaowool Pumpable HS
Chemical Analysis, % weight basis after firing				
Alumina, Al ₂ O ₃	39-43	34	43-47	47-50
Silica, SiO ₂	52-58	66	50-54	47-50
Ferric oxide, Fe ₂ O ₃	-	-	-	0.4-0.7
Other	3-5	-	2-4	2-4

Kaowool® Pumpables

Product Data Sheet



Product Name	Kaowool	Kaowool Pumpable	Kaowool Pumpable	Kaowool Pumpable
Fiber Class	RCF	RCF	RCF	RCF
Physical Properties				
Color	off white	off white	light brown	light brown
Continuous Use Temperature, °F	1900	1900	2400	2800
Continuous Use Temperature, °C	1038	1038	1316	1538
Classification Temperature, °F	2000	2000	2500	2800
Classification Temperature, °C	1093	1093	1371	1538
Density, dried @ 230 °F, pcf	22-26	34-40	23-28	70
Density, dried @ 110°C, kg/m3	352-416	545-641	368-448	1121
Density, wet, pcf	70-75	70-75	73-78	100
Density, wet, kg/m3	1121-1201	1121-1201	1169-1249	1602
Yield, cubic ft / gal	0.13	0.13	0.13	0.13
Yield, cubic m / L	0.004	0.004	0.004	0.004
Shelf life, months	6-12	6-12	6-12	6-12
Modulus of Rupture, MOR dried, psi				
230°F	156	-	-	890
1200°F	76	-	-	-
1500°F	47	-	74	-
1800°F	67	-	-	-
2000°F	-	-	-	530
2250°F	-	-	-	300
2550°F	-	-	-	410
Modulus of Rupture, MOR dried, MPa				
110°C	1.08	-	-	614
649°C	0.52	-	-	-
816°C	0.32	-	0.51	-
982°C	0.46	-	-	-
1093°C	-	-	-	3.65
1232°C	-	-	-	2.07
1399°C	-	-	-	2.83

The product(s) represented are intended for industrial refractory applications. The values and application information in this datasheet are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product, and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials.

Kaowool® Pumpables

Product Data Sheet



Product Name	Kaowool Pumpable	Kaowool Pumpable XTP	Kaowool Pumpable HT	Kaowool Pumpable HS
Compressive strength @ 5% deformation, dried, psi				
230°F	27	-	-	430
1200°F	30	-	-	-
1500°F	35	-	-	-
1800°F	45	75	-	-
2000°F	-	-	-	280
2250°F	-	-	-	270
2550°F	-	-	-	270
Compressive strength @ 5% deformation, dried, MPa				
110°C	0.19	-	-	2.96
649°C	0.21	-	-	-
816°C	0.24	-	-	-
982°C	0.31	0.52	-	-
1093°C	-	-	-	1.93
1232°C	-	-	-	1.86
1399°C	-	-	-	1.86
Compressive strength @ 10% deformation, dried, psi				
230°F	44	-	-	-
1200°F	44	-	-	-
1500°F	54	-	-	-
1800°F	68	-	-	-
Compressive strength @ 10% deformation, dried, MPa				
110°C	0.3	-	-	-
649°C	0.3	-	-	-
816°C	0.37	-	-	-
982°C	0.49	-	-	-

The product(s) represented are intended for industrial refractory applications. The values and application information in this datasheet are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product, and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials.

Kaowool® Pumpables

Product Data Sheet



Product Name	Kaowool Pumpable	Kaowool Pumpable XTP	Kaowool Pumpable HT	Kaowool Pumpable HS
Thermal Conductivity, BTU.in/hr.ft2, per ASTM C201				
300°F	-	0.5	-	-
500°F	0.5	-	0.5	-
700°F	-	0.7	-	-
1000°F	0.7	-	0.7	-
1100°F	-	1.1	-	-
1500°F	1	-	-	-
Thermal Conductivity, Wm.K, per ASTM C201				
149°C	-	0.07	-	-
260°C	0.07	-	0.07	-
371°C	-	0.1	-	-
538°C	0.1	-	0.1	-
593°C	-	0.16	-	-
816°C	0.14	-	0.14	-

Products	5 gallon pail
Kaowool Pumpable	x
Kaowool Pumpable XTP	x
Kaowool Pumpable HT	x
Kaowool Pumpable HS	x

The product(s) represented are intended for industrial refractory applications. The values and application information in this datasheet are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product, and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials.