


JM[®] Insulating Firebrick Series

Product Data Sheet



Product Description

The JM Insulating Firebrick (IFB) series are industry leaders in applications such as Petrochemicals, Metals, Ceramics, and Glass, where the ability to operate in environments with a classification temperature up to 1650°C (3000°F) is critical.

JM IFB series are manufactured from high-purity refractory clays, with graduated additions of alumina for the higher temperature products and a carefully graded organic filler, which burns out during manufacture to give a uniform, controlled pore structure.

Each grade is formulated to meet specific thermal and physical requirements and are machined to precise tolerances on all six faces.

Our IFB range - JM, K, and TJM - delivers big energy savings for many markets, and our global manufacturing footprint enables Morgan to meet your regional and global application demands.

A comprehensive range of mortars are also available to suit the different grades of brick.

Features

- Low thermal conductivity
- Low heat storage
- High purity, consistent raw materials
- Low iron and alkali flux content gives high refractoriness under load in operating conditions
- High hot compressive strength
- Tight dimensional tolerances
- Large bricks or slabs and special shapes available
- Purpose-designed packaging protects bricks in transit and facilitates on-site handling

Applications

- Aluminium anode bake furnaces, primary electrolytic cells, holding and melting furnaces and secondary remelt furnaces
- Petrochemical heaters, flues, refining vessels and reactor chambers
- Iron and steel industry, hot blast furnace stoves, hot blast main and bustle pipe, heat treatment and galvanizing furnaces
- Metals, heat treatment and atmosphere furnaces
- Ceramic industry, including kilns for domestic and laboratory use
- Glass industry
- Hot Face and Backup insulation in industrial furnaces

JM[®] Insulating Firebrick Series

Product Data Sheet



Properties	JM23	JM25	JM26	JM28	JM30	JM30HA	JM26HD
ISO 2245 Classification	125 0.5L	-	140 0.8L	150 0.9L	160 1.0L	-	-
Classification Temperature, °C (°F)	1260 (2300)	1350 (2450)	1430 (2600)	1540 (2800)	1650 (3000)	1650 (3000)	1400 (2600)
Brick markings	23	25	26	28	30	30 HA	26-HD
Density, kg/m ³ (pcf), ASTM C134	480 (30.0)	770 (48.0)	800 (49.9)	890 (55.5)	1020 (63.6)	1250 (78.0)	920 (57.4)
Modulus of rupture, MPa (psi), ASTM C133	1 (145)	1 (145)	1.5 (217.5)	1.8 (261)	2 (290)	2.1 (304.6)	2.2 (319)
Cold Crushing strength, MPa (psi), ASTM C133	1 (145)	1.3 (188.5)	1.6 (232)	2.1 (304.5)	2.3 (333.5)	3.2 (464.1)	3.5 (507.5)
Reversible Linear Thermal Expansion, max. %	0.5	0.4	0.5	0.6	0.6	-	-
Linear Shrinkage, % after 24 hours soaking, ASTM C210							
1230°C (2246°F)	-0.4	-	-	-	-	-	-
1290°C (2354°F)	-	-0.2	-	-	-	-	-
1400°C (2552°F)	-	-	-0.2	-	-	-	-0.3
1510°C (2750°F)	-	-	-	-0.4	-	-	-
1620°C (2948°F)	-	-	-	-	-0.6	±0.1	-
Chemical Analysis, %							
Alumina, Al ₂ O ₃	37	58	58	67.1	71.5	79.7	58
Silica, SiO ₂	45.5	38	38.8	30.0	26.9	18.0	38.8
Iron Oxide, Fe ₂ O ₃	0.9	0.9	0.8	0.6	0.5	0.40	0.8
Titania, TiO ₂	0.5	0.4	0.3	0.5	0.4	0.3	0.3
Lime, CaO	15.2	0.2	0.1	0.1	0.2	0.1	0.1
Alkali as, MgO + Na ₂ O + K ₂ O	1.9	1.8	1.9	1.0	0.8	0.7	1.9
Thermal Conductivity, W/m·K, ASTM C-182							
400°C	0.14	0.24	0.25	0.3	0.36	0.47	0.33
600°C	0.16	0.25	0.27	0.32	0.37	0.48	0.35
800°C	0.17	0.27	0.3	0.34	0.37	0.49	0.37
1000°C	0.19	0.3	0.33	0.36	0.38	0.5	0.39
1100°C	-	-	0.33	0.36	0.39	0.51	-
1200°C	-	-	-	-	0.39	-	-
Thermal Conductivity, BTU·in/hr·ft ² ·°F, ASTM C-182							
752°F	0.97	1.67	1.73	2.08	2.50	3.26	2.29
1112°F	1.11	1.73	1.87	2.22	2.57	3.33	2.43
1472°F	1.18	1.87	2.08	2.36	2.57	3.40	2.57
1832°F	1.32	2.08	2.29	2.50	2.64	3.47	2.71
2012°F	-	-	2.29	2.50	2.71	3.54	-
2192°F	-	-	-	-	2.71	-	-

Whilst the values and application information in this datasheet are typical, they are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials - Thermal Ceramics.