Kao-Tuff™ FS Monolithic

Product Data Sheet

Product Description

Kao-Tuff FS is a medium-weight, fused silica based monolithic with excellent thermal shock resistance. It is installed by standard vibratory casting techniques.

Instructions for Using

Casting: Highest strength is obtained with a monolithic refractory by using the least amount of clean mixing water which will allow thorough working of material into place by vibrating or rodding. A mechanical mixer is required for proper placement (paddle type mortar mixer best suited). After adding the recommended amount of water to achieve a ball-in-hand consistency, wet mix for 4-6 minutes. Place material within 30 minutes after mixing.

Precautions: Watertight forms must be used when placing material. All porous surfaces that will come in contact with the material must be waterproofed with a suitable coating or membrane. For maximum strength, cure 24 hours in a damp condition before initial heat-up. Keep freshly placed monolithic warm during cold weather, ideally between 16°C and 27°C (60°F and 80°F) until wet curing is complete. New monolithic installations must be heated slowly the first time.

For detailed installation instructions and commissioning schedules, please contact your Morgan Advanced Materials-Thermal Ceramics representative.

Properties	Kao-Tuff FS
Region of Manufacture	Americas
Bond type	Hydraulic
Raw material base	Fused Silica
Method of installation	Vibratory Cast
Maximum grain size, mm	6
Maximum service temperature, °C (°F)	1316 (2400)
Net material requirement, kg/m^3 (pcf)	2019 (126)
Water addition, % by weight	
casting by vibrating	5.5-6.5
Packaging in bags, kg (lbs)	25 (55)

The product(s) represented are intended for industrial refractory applications. The values and application information in this datasheet are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product, and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials.

Kao-Tuff™ FS Monolithic

Product Data Sheet

Properties	Kao-Tuff FS
Bulk Density, kg/m^3 (pcf), ASTM C134	
dried 24 hours @ 105°C (220°F)	1986-2147 (124-134)
fired 5 hours @ 816°C (1500°F)	1938-2098 (121-131)
Modulus of Rupture, MPa (psi), ASTM C133	
dried 24 hours @ 105°C (220°F)	4.8-8.3 (700-1200)
fired 5 hours @ 816°C (1500°F)	4.1-6.9 (600-1000)
Cold Crushing Strength, MPa (psi), ASTM C133	
dried 24 hours @ 105°C (220°F)	41.4-65.5 (6000-9500)
fired 5 hours @ 816°C (1500°F)	34.5-62.1 (5000-9000)
fired 5 hours @ maximum service temperature °C (°F)	41.4-69.0 (6000-10000)
Permanent Linear Change, %, ASTM C113	
dried 24 hours @ 105°C (220°F)	0 to -0.2
fired 5 hours @ 816°C (1500°F)	-0.1 to -0.3
fired 5 hours @ maximum service temperature °C (°F)	-0.2 to -0.5
Abrasion loss, cm^3, ASTM C704	
fired 5 hours @ 816°C (1500°F)	12-22
Chemical Analysis, %, Calcined Basis	
Alumina, Al_2O_3	21
Silica, SiO_2	75
Iron Oxide, Fe_2O_3	0.2
Titania, TiO_2	0.4
Lime, CaO	2.3
Magnesia, MgO	0.1
Alkali as, $Na_2O + K_2O$	0.1
Thermal Conductivity, W.m•K (BTU•in/hr•ft^2•°F) , ASTM C417	
260°C (500°F)	1.21 (8.4)
538°C (1000°F)	1.34 (9.3)
816°C (1500°F)	1.41 (9.8)
1093°C (2000°F)	1.43 (9.9)

Storage and Shelf Life

- Monolithics should be stored in a dry, well-ventilated area and held off the ground on pallets ideally with the original packaging intact. Keep out of rain and damp conditions.
- Normal shelf life is 9 months from date of manufacture when properly stored.

The product(s) represented are intended for industrial refractory applications. The values and application information in this datasheet are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product, and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials.

www.morganthermalceramics.com
Email: marketing.tc@morganplc.com
Thermal Ceramics is a business of Morgan Advanced Materials